



KAPCI
COATINGS

For professional use only

Issue date:
July 2010

31

Kapci 500

Nitrocellulose topcoat

Product description

Kapci 500 is a high gloss paint based on nitrocellulose resin. Kapci 500 is a fast drying topcoat with very good coverage. It is used for outdoor and indoor repair. The product is not recommended for all car repairs.

Suitable substrates

Kapci 500 can be applied over old paints in good conditions, NC putties, 1K fillers and 2K fillers.









The surface should be properly prepared and thoroughly degreased with Kapci 605 Degreaser prior to painting.

These products are for the professional painting of automotive vehicles only after reference to the manufacturer's Material Safety Data Sheets

www.kapci.com

Kapci Car
Refinishes
System

Product Process

Product	Kapci 500 NC topcoat
Thinner	Kapci 525 NC Thinner
	Mixing ratio by volume: Kapci 500 1 Kapci 525 1 Use measuring stick No°2
	18-22 sec (F4 at 20°C)
	Pot life: unlimited
	Fluid tip 1.3 mm Pressure: 3.0-3.5 bar/ 45-50 psi inlet NOTE: Refer to manufacturer's recommendation.
	Fluid tip 1.3 mm Pressure: 2 bar/30 psi inlet NOTE: Refer to manufacturer's recommendation.
	2 full coats Recommended dry film thickness is 40-50 microns.
	5-10 minutes between coats
	Drying time Handling: 20°C 40°C 60°C 30 min 20 min 15 min

Health and Safety

1. For full Health and Safety information please refer to Material Safety Data Sheet;
2. Observe the precautionary notices displayed on the container;
3. Goggles and suitable protective equipment must be worn while using these products;
4. Good ventilation must be provided in the working environment;