



**KAPCI**  
COATINGS

For professional use only

Issue: March 2016  
Superseded: July 2010

## Kapci 9999CN 2K MS Acrylic Clearcoat

### Product description

Kapci 9999CN is a 2K medium solid acrylic clearcoat especially formulated for applying over Kapci basecoats. It delivers good gloss when is used in conjunction with Kapci MS hardeners and Kapci 2K Thinners.

### Substrates

Kapci 9999CN clearcoat should be applied over:

1. Kapcibase solvent-based basecoat
2. Properly prepared paint work in good conditions

Existing job should be properly sanded and degreased. For cleaning and degreasing the surface prior to applying the basecoat, it is recommended to use Kapci Degreaser 605.

### Application



**Mixing ratio:**


100:50:30  
(2:1:0.6)

100% Kapci 9999CN MS Clearcoat

50% Kapci MS Hardeners: 653 Extra Fast, 652 Fast, 651 Normal or 656 Slow

30% Kapci 2K Thinners: 600F Fast, 600 Normal, 601 Slow or 602 Extra Slow

Note: Select appropriate thinner and hardener according to ambient temperature, air movement, and size of the surface to be clearcoated.



Use mixing ruler

These products are for the professional painting of automotive vehicles only after reference to the manufacturer's Material Safety Data Sheets (MSDS)


Rev (01) 03/2016




**KAPCI**  
COATINGS

For professional use only


Issue: March 2016  
Superseded: July 2010



**Application viscosity:**  
15-18 s (DIN4/20°C)




**Pot life:**  
3 h at 20°C




**Spraygun tips:**  
1.3 mm  
Conventional:  
3.0-3.5 bar/45-50 psi inlet  
HVLP: 2 bar/30 psi inlet

Refer to the spraygun manufacturer's recommendation.



**Number of coats:**  
Apply 2 normal coats.

Total dry film thickness 50-60 microns.



**Flash off time:**  
5-10 min/20°C between coats  
15-20 min/20°C before baking



**Drying time:**  
12 h/20°C  
30 min/60°C



**IR Drying:**  
Short wave\*: 10-15 min  
\*Guideline for IR equipment. Refer to the IR equipment manufacturer's instruction for sets up.

### General notes

#### **Choice of hardener**

Kapci offers a range of hardeners to meet every type and size of car refinish under all conditions.

The recommendations below are for guidance only:

Kapci 653 Extra Fast hardener is recommended for temperatures below 20°C and for small size of repair.

Rev (01) 03/2016



**KAPCI**  
COATINGS

**For professional use only**

**Issue: March 2016**  
**Superseded: July 2010**

Kapci 652 Fast hardener is used for medium sized repair and for temperatures up to 25°C.  
Kapci 651 Normal hardener is suitable for large areas, i.e. for all repairs at temperatures up to 30°C.  
Kapci 656 Slow hardener should be used when the temperature exceeds 30°C.

***Use of Kapci 6510 Accelerator***

The drying time of Kapci 9999CN clearcoat can be accelerated by using Kapci 6510 Accelerator (see relevant TDS). Kapci 6510 is added in the amount of 1-4 mass% calculated on the total mass of the clearcoat and the hardener. Note that the addition of Kapci 6510 will reduce pot life.

***Rectification and polishing***

Kapci 9999CN clearcoat does not require polishing as it offers excellent gloss. In a case that some dirt has occurred, denib with P1500 or finer and polish by machine using a high quality polish. Polishing is easiest up to 24 h after the drying time.

***Other tips***

1. For optimum application, ensure that both spray booth temperature and paint temperature are between 20°C and 25°C.
2. Clean the spraygun thoroughly immediately after use of 2K products.

**Health and Safety**

1. For full Health and Safety information please refer to Material Safety Data Sheet (MSDS).
2. Observe the precautionary notices displayed on the container.
3. Goggles and suitable protective equipment must be worn while using these products.
4. Good ventilation must be provided in the working environment.

**IMPORTANT NOTE:** These products are for professional use only. The information in this Technical Data Sheet is based on our best knowledge and given for information purposes only without any obligation as we do not have control over the quality and conditions of the surface, or over many factors affecting the use and application of the product. Always read the Material Safety Data Sheet and the Technical Data Sheet for this product if available.

Rev (01) 03/2016