



KAPCI
COATINGS

Issue date: May 2017
Superseded: April 2015

Kapci 2000 MV NC Sealer

Product properties

Kapci 2000 MV is a medium viscosity fast drying nitrocellulose-based transparent sealer used for the protection of furniture, wooden articles, and interior woodwork. It offers good filling properties, good leveling, fast drying, and easy sandability.

Theoretical coverage: 6-8 m²/kg per a coat

Products for application

Kapci 2000 MV NC Sealer
Kapci 525 NC Thinner

Substrate and surface preparation

Sand the surface of solid wood with P80 or P120 sanding paper. Blow off dust and wipe off contaminants (grease, oil, etc.) prior to applying Kapci 2000 MV NC Sealer.

Mixing ratio by weight

Kapci 2000 MV NC Sealer Transparent	100%
Kapci 525 NC Thinner	max 100%

Application

Kapci 2000 MV NC sealer can be applied by spraying or by brush in 2 coats. If more coats are required, allow 5-10 minutes of flash off time between coats.

Kapci 2000 MV NC sealer can be overcoated with Kapci 1K matt/gloss clearcoat.

Drying time at 25°C

Dry dust free: 10-15 min
Dry to sand: 2-4 h

Color

Transparent light color is available.

Rev (02) 05/2017



KAPCI
COATINGS

Issue date: May 2017
Superseded: April 2015

Other tips

1. Practical coverage depends on several factors including shape, roughness and porosity of the object to be painted, spraying equipment used, application methods, application conditions, film thickness, etc.
2. For best results, it is always recommended to test the products on scrap pieces of wood before start paint job.

Shelf life

3 years from production date stored in original packaging at normal conditions.

Health and Safety

1. For full Health and Safety information please refer to the Material Safety Data Sheet.
2. Observe the precautionary notices displayed on the container.
3. Good ventilation must be provided in the working environment.

IMPORTANT NOTE: The information in this technical data sheet is based on our best knowledge and given for information purposes only without any obligation as we do not have control over the quality and conditions of the surface, or over many factors affecting the use and the application of the product. Always read the Materials Safety Data Sheet and the Technical Data Sheet for this product if available.

Rev (02) 05/2017