



KAPCI
COATINGS

Issue date: January 2018
Superseded: August 2015

Kapci 2180 Aqua Sanding Sealer For Interior

Product properties

Kapci 2180 Aqua Sanding Sealer is a waterborne sealer which provides optimal resistance against household chemicals. The product is recommended for kitchen, bathroom cabinets, furniture, and interior woodworks.

Theoretical coverage: 4-5 m²/l per a coat

Products for application

Kapci 2180 Aqua Sanding Sealer
Deionized Water (DI Water), Potable Water


Note: It is always recommended to add DI water rather than potable water

Substrate and surface preparation

Kapci 2180 Aqua Sanding Sealer is applied over wooden surfaces previously properly sanded. Sand the surface of solid wood with P80-P120 grit paper. For MDF, plywood or veneer, use finer grit paper P150 or P180. Blow off dust and degrease the surface.

If coloring of wood is required, use Kapci 2800 Wood Stain prior to applying Kapci 2180 Aqua Sanding Sealer.

Application



Mixing ratio:	by spraying	by brush
Kapci 2180 Aqua Sanding Sealer	100%	100%
DI Water or Potable Water	10%	5%



Apply 2 single coats
Spray gun nozzle: 1.8mm
Note: Refer to the spray gun manufacturer's recommendation.



Apply 2 coats



KAPCI
COATINGS

Issue date: January 2018
Superseded: August 2015



Dry to touch: 20-30 min/25°C
Dry to sand: 2 h/°25C

Other tips

Practical coverage depends on several factors including shape, roughness and porosity of the object to be painted, spraying equipment used, application methods, application conditions, film thickness, etc.

Shelf life

1 year from production date stored in original packaging at normal conditions. Store the product from 5°C to 35°C.

Health and Safety

1. For full Health and Safety information please refer to the Material Safety Data Sheet.
2. Observe the precautionary notices displayed on the container.
3. Good ventilation must be provided in the working environment.

IMPORTANT NOTE: The information in this technical data sheet is based on our best knowledge and given for information purposes only without any obligation as we do not have control over the quality and conditions of the surface, or over many factors affecting the use and the application of the product. Always read the Materials Safety Data Sheet and the Technical Data Sheet for this product if available.

Rev (02) 01/2018