



KAPCI
COATINGS

Issue date: May 2017
Superseded: May 2015

Kapci 2202 PE White Sealer

Product properties

Kapci 2202 is a paraffin-free polyester white sealer used for the protection of furniture, wooden articles, and interior wood work. It has excellent filling and sanding properties, good leveling, and high build. It is particularly recommended for MDF and chipboards in combination with polyurethane finishes where high quality surface treatment is required.

Theoretical coverage: 4-5 m²/kg per a coat

Products for application

Kapci 2202 PE White Sealer
Kapci 2210 Accelerator
Kapci 2215 Catalyst
Kapci 2220 Thinner

Substrate and surface preparation

Kapci 2202 is designed for application over different types of wooden substrate and is particularly recommended for MDF and chipboards in conjunction with polyurethane finishes.

For obtaining optimum results, it is recommended to apply Kapci 2100 Polyurethane Insulator prior to applying Kapci 2202.

In case of applying Kapci 2202 over porous and resinous types of wood (rosewood, teakwood, mansonia, etc.), the use of the insulator is required. Kapci 2100 insulator must be left to dry for 2-3 hours before the application of Kapci 2202 PE White Sealer.


Sand the surface of solid wood with P80-P120 grit paper. For MDF, plywood and veneer, use finer grit paper P150 or P180. Blow off dust and degrease the surface.



KAPCI
COATINGS

Issue date: May 2017
Superseded: May 2015

Application



Mixing ratio: 100:2:2:20-30
Accelerator: Kapci 2210
Catalyst: Kapci 2215
PE Thinner: Kapci 2220

Note: Mix Kapci 2202 white sealer with Kapci 2210 accelerator prior to adding Kapci 2215 catalyst, then add Kapci 2220 Thinner. Do not mix together accelerator Kapci 2210 with catalyst Kapci 2215.



Pot life: 15 minutes.
Apply 2 single coats.
Spray gun nozzle: 2.5 mm
Note: Refer to the spray gun manufacturer's recommendation.



Dry to sand: Next day



Sand with P220 grit paper followed with P320 and finish with P500

Precautions

As polyesters products are more difficult to use than conventional paints, precautions and care need to be taken prior to and during the application:

1. Extreme care should be taken when measure the catalyst. Do not add less or more the catalyst as it will adversely affect the final result.
2. Follow the mixing instructions and order of adding of the mixing components. The Accelerator and catalyst must not be mixed directly with each other!
3. Ensure correct storage and handling of the accelerator and catalyst. They are inflammable in direct contact.
4. Avoid storage in hot conditions.
5. Be aware of short pot life and short shelf life of the product.



KAPCI
COATINGS

Issue date: May 2017
Superseded: May 2015

Other tips

Practical coverage depends on several factors including shape, roughness and porosity of the object to be painted, spraying equipment used, application methods, application conditions, film thickness, etc.

Shelf life

1 year from production date stored in original packaging at normal conditions. Avoid storage in hot conditions and direct exposure to sun.

Health and Safety

1. For full Health and Safety information please refer to the Material Safety Data Sheet.
2. Observe the precautionary notices displayed on the container.
3. Good ventilation must be provided in the working environment.

IMPORTANT NOTE: The information in this technical data sheet is based on our best knowledge and given for information purposes only without any obligation as we do not have control over the quality and conditions of the surface, or over many factors affecting the use and the application of the product. Always read the Materials Safety Data Sheet and the Technical Data Sheet for this product if available.

Rev (02) 05/2017