



KAPCI
COATINGS

Wood Coatings

www.kapci.com

01

Kapci 200 NC Gloss

1- Product properties

Kapci 200 Gloss is a high gloss nitrocellulose based paint with excellent hardness, good coverage, high gloss, good softness to touch and good bending.

Viscosity	40 - 45 sec / Ford cup 8 at 25°C
Density	0.97 - 1.25 g/cm ³
Coverage	5 - 7 m ² /kg

2- Products for application

Kapci 200 NC Gloss
Kapci 525 NC Thinner

3- Suitable substrate and surface preparation

Kapci 200 Gloss is suitable for application over 1K and 2K fillers or NC putty. Surface must be degreased using Kapci 605.

Recommended sanding:

- 1K and 2K filler with paper P320 – P400 mechanical or dry manual sanding;
- NC putty with paper P320 – P400 mechanical or dry manual sanding;

4- Method of application

By spray or by curtain coater, thinned with Kapci 525 from 80% up to 100% to reach correct application viscosity. Kapci 200 can be applied in 2-3 coats allowing flash off time for 5-10 minutes between coats.

5- Drying at 25°C

Dust Free	20 min
Complete dry	24 hrs

6- Color

According to Kapci color chart.

7- Expiry

5 years from production date in original container at normal temperature.

8- Material safety data

When use these products it is required to comply with the national regulations for health and safety.

Wood
Coatings