



KAPCI
COATINGS

Wood Coatings

www.kapci.com

12

Kapci 2010 Polyurethane Varnish

1- Product properties

Kapci 2010 is a high gloss clear coat that gives outstanding weathering, chemical and high scratch resistance. It is suitable for applying over wood, parquet floors, windows, tires, boats, kitchens.

Viscosity	72 ± 2 sec / Ford cup 6 at 25°C
Density	0.9 – 0.92 g/cm ³
Solid Content	58 ± 2 %
Coverage	11 – 14 m ² /kg
Sanding	High Gloss

2- Products for application

Kapci 2010 PU Varnish
Kapci 555 Thinner

3- Suitable substrate and surface preparation

For new or previously painted surfaces. It can be applied on wood after proper priming. Surface must be dry, smooth and clean from dust, oils and greases. In some cases priming with Kapci 2000, Kapci 2150 or Kapci 2200 is required.

4- Method of application

By spray gun or brush. Add 30% of Kapci 555 thinner.

5- Drying at 25°C

Dry to touch	2 hrs
Hard dry	24 hrs

6- Expiry

3 years from production date in original container at normal temperature.

7- Material safety data

When use these products it is required to comply with the national regulations for health and safety.

Wood
Coatings