



KAPCI
COATINGS

Wood Coatings

www.kapci.com

16

Kapci 2150 Polyurethane Clear Sealer

1- Product properties

Kapci 2150 is a transparent polyurethane sealer with excellent adhesion, sandability and coverage.

Viscosity	70 ± 2 sec / Ford cup 4 at 25°C
Density	0.97 ± 0.02 g/cm ³
Solid Content	42 ± 2%
Coverage	5 – 7 m ² /kg

2- Products for application

Kapci 2150 PU Clear Sealer
Kapci 2155 Hardener for PU Clear Sealer
Kapci 2450 PU Thinner-normal
Kapci 2460 PU Thinner-slow

NOTE: Kapci 2460 slow thinner is recommended for high temperature.

3- Suitable substrate and surface preparation

Product is suitable for application over almost any type of wood.

4- Mixing ratio

	By Volume
Kapci 2150	2
Kapci 2155	1
Kapci 2450 (or 2460)	20-30%

5- Pot life

2 - 3 hours at 20°C

Wood
Coatings

6- Method of application

Kapci 2150 can be applied by spraying or by brush, in more than one coat. Flash off time between coats is 10-20 minutes.

Kapci 2150 can be overcoated with any Kapci clearcoat.

7- Drying at 25°C

Dust Free 15-30 min

Hard dry 2-4 hrs

Sandable 4-6 hrs

8- Equipment cleaning

Spraying equipment must be cleaned immediately after use. Thinners used for thinning of nitrocellulose paints can be used.

9- Expiry

3 years from production date in original container at 20°C.

10- Material safety data

When use these products it is required to comply with the national regulations for health and safety.