



**KAPCI**  
**COATINGS**

Wood Coatings

[www.kapci.com](http://www.kapci.com)

18

# Kapci 2202 Polyester White Sealer

## 1- Product properties

Kapci 2202 is a white polyester sealer with excellent filling and sanding properties, good leveling and coverage. It may be applied over different types of wooden substrates.

<b>Viscosity</b>	13 ± 2 sec / Ford cup 8 at 25°C
<b>Density</b>	1.38 ± 0.02 g/cm <sup>3</sup>
<b>Solid Content</b>	75 ± 2%
<b>Coverage</b>	4 – 5 m <sup>2</sup> /kg

## 2- Products for application

Kapci 2202 PE White Sealer  
Kapci 2210 Accelerator  
Kapci 2215 Catalyst  
Kapci 2220 Thinner

## 3- Suitable substrate and surface preparation

Kapci 2202 is designed for application over different types of wooden substrate. However, to obtain optimum results it is recommended to apply Kapci 2100 Polyurethane Insulator prior to applying Kapci 2202.

When applying Kapci 2202 over resinous types of wood- rosewood, teakwood and mansonia, the use of the insulator is required. The insulator must be left to dry for 3–4 hours before the application of Kapci 2202.

## 4- Mixing ratio

	By Volume %
Kapci 2202	100
Kapci 2210	2
Kapci 2215	2
Kapci 2220	20-30

Wood  
Coatings

## 5- Pot life

30-40 minutes at 20°C

## 6- Method of application

Apply 2 single coats of Kapci 2202 PE White Sealer by spraying. Apply 200-250 g/m<sup>2</sup> per each coat and allow flash off time between coats 1-3 h.

## 7- Drying at 25°C

Dust Free	1.5 hrs
Tack free	2.5 hrs
Hard dry	18 hrs
Sandable	18 hrs

## 8- Equipment cleaning

Spraying equipment must be cleaned immediately after use. Thinners used for thinning of nitrocellulose paints can be used.

## 9- Expiry

1 year from production date in original container at 20°C.

## 10- Material safety data

When use these products it is required to comply with the national regulations for health and safety.