



## Wood Coatings

Issue date: July 2010

# Latico 6800 Polyester Sealer for wood

### Product description

Latico 6800 is a transparent polyester sealer with good filling and sanding properties, good leveling and coverage. It may be applied over different types of wooden substrates.

Viscosity	25 ± 2 sec / Ford cup 8 at 25°C
Solid Content	63 ± 2%
Density	1.06 ± 0.02 g/cm <sup>3</sup>
Coverage	4- 5 m <sup>2</sup> /kg

### Products for application

Latico 6800 PE Sealer  
Kapci 2210 Accelerator  
Kapci 2215 Catalyst  
Kapci 2220 Thinner

### Substrates and preparation

Latico 6800 is designed for application over different types of wooden substrate. However, to obtain optimum results it is recommended to apply Kapci 2100 Polyurethane Insulator prior to applying Latico 6800. When applying Latico 6800 over resinous types of wood-rosewood, teakwood and mansonina, the use of the insulator is required. The insulator must be left to dry for 3–4 hours before the application of Latico 6800.

### Mixing ratio

Latico 6800	100%
Kapci 2210	2%
Kapci 2215	2%
Kapci 2220	20-30%

Pot life at 20°C: 30-40 minutes



## Wood Coatings

### Application

Apply Latico 6800 PE Sealer by spraying:

Spray gun nozzle: 2.0-3.0 mm;

Conventional spray gun: pressure 2.5-3.0 bar;

HVLP spray gun: pressure 2.0 bar;

It is recommended to apply Latico 6800 in 2 single coats. Apply 200- 250 g/m<sup>2</sup> of the products per each coat and allow flash off time between coats 15-20 minutes.

Drying at 25°C

Tack free 2.5 h

Sandable 24 h

### Sanding

Manual sanding: P320-P400

Machine sanding: P240-P400

### Expiry

1 year from production date in original container at 20°C.

### Health and safety

For full Health and Safety information please refer to Material Safety Data Sheet. Observe the precautionary notices displayed on the container.